


Information

Thickness ⁽¹⁾		Design Weight ⁽²⁾			
		AAC-4		AAC-6	
in ⁽¹⁾	in*	lb/ft ²	lb/ft	lb/ft ²	lb/ft
4	3.937	12.29	24.59	14.75	29.51
5	4.921	15.36	30.74	18.43	36.89
6	5.906	18.43	36.89	22.12	44.27
7	6.889	21.51	43.04	25.81	51.65
8	7.874	24.58	49.19	29.49	59.03
10	9.843	30.72	61.48	36.87	73.78
12	11.811	36.87	73.78	44.24	88.54

⁽¹⁾ Nominal dimension, ⁽²⁾ Values consider material's moisture content, *Exact dimension.



AAC-4	
Design Weight ⁽²⁾	37.42 lb/ft ³
Minimum Compressive Strength	580 lb/in ²
AAC-6	
Design Weight ⁽²⁾	44.95 lb/ft ³
Minimum Compressive Strength	870 lb/in ²

Installation Detail

Contact us for more information:

Litecrete, Inc.
(210)402-3223 / 1 877 41 HEBEL (1 877 41 43235)
hebel-usa@hebel.mx
www.hebel-usa.com